

LOCTITE ABLESTIK 45 W1

March 2015

PRODUCT DESCRIPTION

LOCTITE ABLESTIK 45 W1 provides the following product characteristics:

Technology	Epoxy
Appearance (Resin)	Black
Product Benefits	<ul style="list-style-type: none"> • Easy mix ratio • Rigid, semi-rigid, and flexible formulations • Excellent shock and peel resistance
Application	General assembly
Operating Temperature - Semi-rigid	-55 to 90°C

Its variable mix ratio allows for a rigid, semi-rigid, or flexible cured material. It is designed for use where shock and peel resistance are desired. This material adheres well to a variety of substrates including metals, glass, ceramic and plastics.

LOCTITE ABLESTIK 45 W1 can be used with LOCTITE CAT 15:

CATALYST DESCRIPTION

LOCTITE CAT 15 provides the following product characteristics:

Appearance (Catalyst)	Black
Product Benefits	<ul style="list-style-type: none"> • General purpose • Good chemical resistance • Good physical strength
Cure	Room Temperature or Heat Cure
Mix Ratio, by weight - Resin : Hardener Rigid Formula	100 : 50
Mix Ratio, by weight - Resin : Hardener Semi-rigid Formula	100 : 100
Mix Ratio, by weight - Resin : Hardener Flexible Formula	100 : 150

TYPICAL UNCURED PROPERTIES

LOCTITE ABLESTIK 45 W1

Viscosity @ 25 °C, mPa·s (cP)	225,000
Density, g/cm ³	1.59
Shelf Life (from date of manufacture), @ 18 to 25 °C	365
Flash Point - See SDS	

TYPICAL UNCURED PROPERTIES AS MIXED

LOCTITE ABLESTIK 45 W1 with LOCTITE CAT 15

Viscosity @ 25 °C, mPa·s (cP)	40,000
Density, g/cm ³	1.59
Pot Life @ 25°C, hours	2

TYPICAL CURING PERFORMANCE

Cure Schedule

LOCTITE ABLESTIK 45 W1 with LOCTITE CAT 15

8 hours @ 25°C
30 minutes @ 70°C
15 minutes @ 105°C

Bond strength will increase during the first 24 hours following cure.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Semi-rigid Formulation

LOCTITE ABLESTIK 45 W1 with LOCTITE CAT 15

Physical Properties

Hardness, Shore D	65
Flexural Strength	N/mm ² 34 (psi) (4,930)
Young's Modulus, ASTM D638 Unit}	N/mm ² 500 (psi) (72,500)
Impact Strength, ASTM-D-256, J/cm	22
Volume Shrinkage on Cure, %	3.5
Glass Transition Temperature, °C	37
Coefficient of Linear Thermal Expansion, ppm/°C	50
DMA Modulus :	
@ 35°C	124
@ 50°C	21
@ 100°C	13
Water Absorption, %:	
24 hours immersion @ 25 °C	0.98
7 days immersion @ 25 °C	4.1

Electrical Properties

Volume Resistivity @ 25°C, ohm-cm	3.4×10 ¹³
Dielectric Constant / Dissipation Factor:	
@ 0.05 to 1,000	4.0/0.06
Dielectric Strength, ASTM D149, kV/mm	15.6
Surface Resistivity, ohms	3.1×10 ¹⁶

TYPICAL CURED PERFORMANCE AS MIXED

Semi-rigid Formulation

LOCTITE ABLESTIK 45 W1 with LOCTITE CAT 15

Shear Strength :

Tensile Lap Shear Strength	N/mm ² 12 (psi) (1,740)
----------------------------	---------------------------------------

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
2. Mix LOCTITE ABLESTIK 45 W1 in the can in which it is received.
3. Accurately weigh resin and hardener into a clean container in the one of the recommended ratios. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.
4. Mix thoroughly.
5. Application is by brush, knife or roller. Apply and squeeze out excess.
6. To prevent adhesion, use MOLD RELEASE 122 S.
7. Clean up solvent is alcohol, acetone, or methyl ethyl ketone (MEK).
8. NOTE: During storage at room temperature for long periods, it is possible that the viscosity of can increase and may exceed its upper specification limit. The viscosity can be brought back to the normal level by moderate mixing.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} = \text{N/mm}^2$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0