

LOCTITE ABLESTIK 56C CAT 9 KIT

May 2019

PRODUCT DESCRIPTION

LOCTITE ABLESTIK 56C CAT 9 KIT provides the following product characteristics:

Technology	Epoxy
Appearance	Silver
Filler Type	Silver
Components	Two components - requires mixing
Mix Ratio, by weight - Resin : Hardener	100 : 2.5
Product Benefits	<ul style="list-style-type: none"> Electrically conductive Low temperature cure High bond strength Low electrical resistance No-flow characteristics Two components Long shelf life at room temperature Passes NASA outgassing
Cure	Heat Cure
Application	Assembly
Operating Temperature	-60 to 120 °C
Surfaces	Metals, Glass, Ceramics and Plastics

LOCTITE ABLESTIK 56C CAT 9 KIT adhesive is designed to make electrical connections where hot soldering is impractical or to make electrical connections to conductive plastics at locations which cannot be subjected to high temperatures.

LOCTITE ABLESTIK 56C can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

LOCTITE ABLESTIK 56C CAT 9 KIT passes NASA outgassing standards.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Density, g/cm ³	3.15
Shelf Life @ 18 to 25°C, days	365
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Cure Schedule

2 hours @ 50°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Glass Transition Temperature(Tg), °C	80
Coefficient of Thermal Expansion, TMA, 10 ⁻⁶ K ⁻¹ :	
Below Tg	32
Above Tg	120
Extractable Ionic Content, :	
Sodium (Na+)	1
Ammonia (NH3+)	10
Potassium (K+)	1
Chloride (Cl-)	1
Thermal Conductivity , W/(m-K)	3.0
Flexural strength , ASTM D790	N/mm ² 75 (psi) (10,877)

Electrical Properties

Volume Resistivity, ohm-cm	4 x 10 ⁻⁴
----------------------------	----------------------

Outgassing Properties

Total Mass Loss, %	0.23
Collected Volatile Condensable Material, %	0.01

TYPICAL PERFORMANCE OF CURED MATERIAL

Shear Strength

Tensile Strength	N/mm ² 6 (psi) (870)
------------------	------------------------------------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Directions for Use

- Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
- Apply adhesive to surface to be bonded.
- No pressure is required.
- Thinning of LOCTITE ABLESTIK 56C CAT 9 KIT with a small amount of Toluene (10% by weight maximum) can be used where a thin film is applied. Solvent must be evaporated to assure low resistance. The solvent can be added to the catalyst for ease of use..

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 18 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. © denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.11